LANGMUIR Cite This: Langmuir 2018, 34, 5234–5244

Bifunctionalized Redox-Responsive Layers Prepared from a Thiolactone Copolymer

Claire Chattaway,[†] Sabrina Belbekhouche,^{†,§} Filip E. Du Prez,[‡] Karine Glinel,^{*,†} and Sophie Demoustier-Champagne^{*,†}

[†]Institute of Condensed Matter and Nanosciences (Bio and Soft Matter), Université catholique de Louvain, Croix du Sud 1, Box L7.04.02, B-1348 Louvain-la-Neuve, Belgium

[‡]Polymer Chemistry Research Group, Centre of Macromolecular Chemistry (CMaC), Department of Organic and Macromolecular Chemistry, Ghent University, Krijgslaan 281 S4, B-9000 Ghent, Belgium

Supporting Information

ABSTRACT: The development of multifunctional surfaces is of general interest for the fabrication of biomedical, catalytic, microfluidic or biosensing devices. Herein, we report on the preparation of copolymer layers immobilized on gold surface and showing both free thiol and amino groups. These layers are produced by aminolysis of a thiolactone-based copolymer in the presence of a diamine, according to a one-step procedure. The free thiol and amino groups present in the modified copolymer layers can be successfully functionalized with respectively thiolated and carboxylic derivatives, in order to produce bifunctionalized surfaces. In addition, we show that the grafted thiolated derivative can be released by cleavage of the disulfide bond under mild reducing conditions. On the other hand, a side cross-linking reaction



occurring during the grafting process and resulting in the formation of copolymer aggregates on the metal surface is evidenced. The methodology developed for the preparation of these bifunctionalized redox-responsive layers should be advantageously used to produce bioactive surfaces with drug loading/release properties.

INTRODUCTION

The development of coatings containing reactive chemical groups allowing for the subsequent immobilization of various compounds, has been gaining an increasing attention because of their potential use to modify surfaces of various devices involved in biomedical, catalytic, microfluidic, or biosensing applications.¹⁻⁴ In the field of catalysis, for instance, enzymes, chemical ligands, or even substrates are grafted on surfaces enabling to reuse the catalyst for several batches, improving therefore the environmental and the economic impacts of the process.^{4–7} Regarding biomaterials, surfaces grafted with bioadhesive peptides improving cell adhesion,^{8,9} signal proteins directing differenciation,¹⁰ or even antibacterial peptides,¹¹⁻¹³ are highly interesting to improve biocompatibility. Moreover, joining different chemically reactive groups on the same surface enables the possibility of preparing dual- or multifunctionalized materials. For instance, interfaces of implantable materials that simultaneously promote mammalian cells while inhibiting bacterial adhesion have been developed.^{14,15} In catalytic applications, the efficiency of the reaction can be increased by immobilizing two or more active species or enzymes onto the reactive surface.^{16,17} Among the many reported approaches for tailoring the surface properties of a material, 18-20 the sorption of self-assembled monolayers (SAMs) on metals and metal oxides appears as one of the most simple and versatile

methods^{1,19,21,22} allowing to bring a wide variety of chemical functions on the surface such as carboxylic acid, amine, alkane, alcohol, azide, and so on.²³ Moreover, mixed monolayers can be prepared by cografting of alkanethiolates or silanes bearing different terminal chemical functions $^{1,24-26}$ that can be further modified with compounds of interest, such as proteins, peptides, DNA, or small active molecules.^{21,23,27} These multifunctional platforms were shown to be useful for diverse applications such as biosensing, catalysis, or development of model biological surfaces to control cellular processes or study the ligand-protein interaction.^{1,17,23} Research and commercial use of gold coated surfaces and nanoparticles has rapidly expanded in many fields, including biodetection, biomedicine,^{1,28} and so on. SAMs of alkanethiols are probably the most widely studied systems to functionalize gold surfaces.^{1,29,30} However, thiol-based SAMs suffer from several drawbacks. Indeed, alkylthiolates grafted on metallic surface are eventually oxidized to sulfonates (SO_2^{2-}, SO_3^{2-}) and released from the surface.^{21,31} Moreover, exchange can occur between thiol molecules grafted onto the gold surface and alkylthiols present in the surrounding solution, contributing to a poor control of

Received:February 15, 2018Revised:April 17, 2018Published:April 19, 2018

the chemical functionality on the surface.^{31–33} An alternative way to functionalize gold surfaces is based on the use of polythiols. Such polymers can be grafted onto a gold surface through several anchoring points thanks to the presence of multiple thiol groups, which contributes to an increased stability of the elaborated layer.^{34,35} However, polythiols are prone to oxidation under ambient atmosphere, which considerably limits their manipulation. To overcome this drawback, Du Prez and co-workers^{36–43} have recently developed copolymers incorporating thiolactone as a latent thiol functionality. By opening thiolactone cycles using a strong nucleophile such as an amine and thiol groups are liberated and are available to immobilize compounds of interest through a cleavable disulfide bond or via "click chemistry".⁴¹

Recently, we reported the use of these thiolactone-based copolymers as precursors to produce stable polythiol layers onto gold surfaces, according to a one-step process. For this, a gold surface was simply immersed in a copolymer solution in the presence of an amine derivative such as ethanolamine.⁴⁴ It was shown that a part of the thiol groups released from the thiolactone rings during the aminolysis reaction was involved in the formation of stable sulfur—gold bonds between the copolymer chains and the gold surface while another fraction remained free and was further used to immobilize a thiolated derivative of interest through a cleavable disulfide bond. The preparation of redox-responsive copolymer layers leading to the grafting and subsequent release of a thiolated derivative under reducing and oxidizing conditions, respectively, were successfully demonstrated.

In the present work, we report on the production of bifunctionalized gold surfaces, using a thiolactone-based copolymer as starting material (Scheme 1). The most appealing

Scheme 1. Chemical Structure of the Thiolactone-Based Copolymer, P(DMA-co-TlaAm) Used in This Work



feature of the surface functionalization strategy reported herein (Scheme 2) is the simultaneous immobilization of in situ generated polythiols onto gold substrate and the creation of two different types of functional groups (NH₂ and SH) on the copolymer backbone, allowing for the versatile preparation of diverse bifunctionalized redox-responsive surfaces.

For this, the surface functionalization was performed in the presence of a diamine derivative, instead of a monoamine, in order to produce layers showing both free thiol and amine groups (Scheme 2, step 1). While the free thiol groups can be used to immobilize a releasable compound of interest through a cleavable disulfide link, the amino groups can prior or further react with another compound containing a carboxylic acid group thanks to the EDC/sulfo-NHS coupling technique (Scheme 2, step 2). First, the use of a diamine and the influence of the copolymer concentration on the formation of the copolymer layer were studied. In a second step, the modification of amine and thiol groups present in the

copolymer layer was investigated separately (Scheme 3, steps 1 and 1'), prior to the modification of both amine and thiol functions (Scheme 3, steps 1 + 2 or 1' + 2').

EXPERIMENTAL SECTION

Materials. A statistical copolymer based on N,N-dimethyacrylamide (DMA) and thiolactone acrylamide (TlaAm) was synthesized by RAFT polymerization according to a methodology previously described.⁴² This copolymer P(DMA-co-TlAm) had an apparent average molar mass of 32000 g·mol⁻¹ with a dispersity (D) of 1.1, as measured by size exclusion chromatography (SEC) in poly(methyl methacrylate) equivalents and contained 25% of TlaAm units as determined by elemental analysis. Ethanolamine (Sigma-Aldrich, 99%), ethylenediamine (Sigma-Aldrich, 99+%), propylamine (Acros Organics, 98%), FITC-labeled H-RGDK(FITC)-OH peptide (RGD-FITC, $M_w = 863.91 \text{ g} \cdot \text{mol}^{-1}$; Genecust, 99+ %), 4,4,4-trifluorobutyric acid (Sigma-Aldrich, 97%), CSIINFEKL peptide (OVA peptide, M_w = 1066.28 g·mol⁻¹; Genecust, 96+%), glycylglycine (Sigma-Aldrich, 99+ %), N-hydroxysulfosuccinimide sodium salt (sulfo-NHS; Sigma-Aldrich, 98+%), N-(3-(dimethylamino)propyl)-N'-ethylcarbodiimide hydrochloride (EDC; Sigma-Aldrich, 98+%), N-chloro-p-toluenesulfonamide sodium salt trihydrate (CaT; Sigma-Aldrich, 98%), threo-1,4dimercapto-2,3-butanediol (DTT; Sigma-Aldrich, 99+%), L-glutathione reduced (Sigma-Aldrich, 98%), poly(ethylene glycol)methyl ether thiol (PEG-SH; Sigma-Aldrich, $M_n = 2000 \text{ g mol}^{-1}$), rhodamine B-poly(ethylene glycol)-thiol (Rhod B-PEG-SH; Interchim, M_{w} = 3400 g·mol⁻¹), potassium hexacyanoferrate(III) (Sigma-Aldrich, 99+ %), potassium hexacyanoferrate(II) trihydrate (Sigma-Aldrich, 99.5+ %), potassium chloride (KCl; Sigma-Aldrich), 4-(2-hydroxyethyl)-1piperazineethanesulfonic acid (HEPES; Sigma-Aldrich, 99.5+%), 2-(Nmorpholino)ethanesulfonic acid (MES; Sigma-Aldrich, 99.5+%), chloroform (CHCl₃; Sigma-Aldrich, 99.5+ %, anhydrous), ethanol (VWR, HPLC grade), hydrogen peroxide (Sigma-Aldrich, 30%), and sulfuric acid (Sigma-Aldrich) were used as received. Milli-Q water (resistivity 18.2 M Ω ·cm) was obtained from a Merck Millipore system (Milli-Q Reference). Gold surfaces were fabricated in a clean room environment (Winfab platform, Université Catholique de Louvain) by evaporating a 100 nm thick layer of gold on 1×1 cm² silicon wafers (100) precoated with a 5 nm thick layer of chromium. All glassware used for surface modification was cleaned using piranha solution (1:2 v/v mixture of hydrogen peroxide (30%) and sulfuric acid; Caution: piranha solution is extremely reactive and should be handled carefully).

Grafting of P(DMA-co-TlaAm) Copolymer onto Gold Surfaces in the Presence of Amine Derivatives. The 1×1 cm² gold surfaces were first cleaned with water and ethanol, then dried with a stream of N₂. This process was repeated three times. Afterward, surfaces were treated in an UV/ozone chamber (UVO-Cleaner, Jelight) for 20 min, rinsed with ethanol, and dried with a stream of N^2 . The grafting of P(DMA-co-TlaAm) copolymer onto gold surfaces was performed in the presence of either ethanolamine or ethylenediamine. Briefly, 5 mL of 2 or 0.2 mg·mL⁻¹ copolymer solution in chloroform was placed in a glass vial. A solution of the selected amine derivative was added to get 2 or 10 equiv of TlaAm units for ethanolamine and ethylenediamine in the mixture, respectively. This mixture was stirred for 30 s and a freshly cleaned gold surface was rapidly added in the vial. After a contact time of 2 h, the surface was thoroughly rinsed with chloroform, ethanol, and Milli-Q water then dried with a stream of N². To avoid the formation of disulfide bonds between the thiol groups present in the copolymer layer, all the modified surfaces were treated with a DTT solution (2 mM, in 10 mM HEPES, pH 7.2) for 10 min, then rinsed with water and ethanol and eventually dried.

Modification of the Amine Pendent Groups of Copolymer Layers by a Carboxylic Acid Derivative. A gold surface freshly modified with P(DMA-*co*-TlaAm) copolymer in the presence of ethylenediamine was sealed into a Schlenk tube, which was then carefully degassed (i.e., 3 vacuum/Ar filling cycles). At the same time, EDC (16 mM), sulfo-NHS (30 mM) and the carboxylic derivative to be grafted onto the copolymer layer, that is, glycylglycine or 4,4,4trifluorobutyric acid or RGD-FITC (30 mM), were allowed to react

Scheme 2. General Approach to Fabricate Bifunctional Layers on Gold Surfaces^a



^aThe thiolactone moieties of the copolymer are first opened in the presence of a diamine derivative, generating amine and thiol groups onto the copolymer chain (step 1); a part of the released thiol groups is attaching onto the gold surface to form the copolymer layer while the rest of thiol and amine groups are available for subsequent graftings (step 2). While free amine groups are modified with carboxylic acid bearing molecules, the free thiol groups, on the other hand, react with a thiolated derivative through the formation of a cleavable disulfide bond that confers redox-responsive properties to the copolymer layer.

together in degassed MES buffer (0.1 M, pH 6) for 15 min, to get the corresponding activated ester derivative. Afterward, 1 mL of solution of activated glycylglycine or 4,4,4,-trifluorobutyric acid was rapidly added into the Schlenk tube with 4 mL of degassed PBS buffer (0.1 M, pH 8). In the case of the RGD peptide grafting, 200 μ L of solution of activated RGD-FITC and 0.8 mL of degassed PBS buffer were added in the tube. In all cases, the grafting reaction was carried out for 1 h. To estimate the unspecific adsorption of the carboxylic derivatives onto copolymer layers, surfaces grafted with the copolymer were treated in the same conditions but without activation by EDC/sulfo-NHS.

Grafting and Release of Thiolated Compounds on the Pendent Thiol Groups of Copolymer Layers. Fluorescent Rhod B-PEG-SH, PEG-SH or OVA peptide were immobilized onto the free thiol groups of P(DMA-*co*-TlaAm) layers prepared in the presence of ethylenediamine, through the formation of disulfide bonds. For this, a 1×1 cm² gold surface freshly modified with the thiolactone copolymer was placed in a 2 cm diameter Petri dish. The thiolated compound to be grafted on the free thiol groups of the copolymer layer was dissolved in 1 mL of MES buffer (10 mM, pH 6) at a concentration of 0.3 mM and 100 μ L of this solution was deposited onto the gold surface. Then, 1 mL of a 2 mM CaT solution in MES buffer (10 mM, pH 6) was added. After a contact time of 2 min, the surface was thoroughly rinsed with ethanol then Milli-Q water.

To release the grafted thiolated compound from the copolymer layer, the surface was subsequently treated under reductive conditions. For this, the surface was placed for 20 min either in a DTT (2 mM) solution or a L-glutathione (10 mM) solution. Both solutions were buffered with HEPES (10 mM) at pH 7.2.

Characterization Techniques. X-ray Photoelectron Spectroscopy (XPS). The XPS measurements were performed on a SSX 100/206 photoelectron spectrometer from Surface Science Instruments (U.S.A.) equipped with a monochromatized microfocused Al X-ray source (powered at 20 mA and 10 kV). The pressure in the analysis chamber was around 10^{-6} Pa. The angle between the surface normal and the axis of the analyzer lens was 55° . The analyzed area was approximately 1.4 mm², and the pass energy was set at 150 eV. In these conditions, the full width at half-maximum (fwhm) of the Au $4f_{7/2}$ peak of a clean gold standard sample was about 1.6 eV. A flood gun set at 8 eV and a Ni grid placed at 3 mm above the sample surface were used for charge stabilization. A survey spectrum was first acquired with a step of 1 eV. Then the following sequence of narrow spectra was recorded with a step of 0.1 eV: C 1s, O 1s, N 1s, F 1s (whenever a fluorine-containing sample was used), S 2p, and Au 4f peaks and C 1s again to check the stability of charge compensation with time. The C-(C,H) component of the C 1s peak has been fixed to 284.8 eV to set the binding energy scale. Data treatment was performed with the CasaXPS program (Casa Software Ltd., U.K.). The spectra were decomposed with the least-squares fitting routine provided by the software using a Gaussian/Lorentzian (85/15) product function and after subtraction of a nonlinear baseline. Molar fractions were calculated using peak areas measured after linear background subtraction and normalized on the basis of the acquisition parameters and sensitivity and transmission factors provided by the manufacturer.

Electrochemical Impedance Spectroscopy (ElS). EIS characterization of the grafted layers was performed with a CHInstrument potentiostat 660B. The measurements were carried out at room temperature in a one-compartment Teflon cell equipped with a platinum counter electrode, an Ag/AgCl reference electrode and the modified gold surface as a working electrode. The barrier properties of the grafted layers were evaluated by measuring the electron transfer reaction on the modified surface using a potassium ferrocyanide redox probe. The electrolytic solution contained equal concentrations of both oxidized and reduced forms of the redox couple namely, 1 mM potassium ferrocyanide(II) (K_4 Fe(CN)₆) and potassium ferrocyanide-(III) (K_3 Fe(CN)₆) solubilized in 0.1 M KCl. All electrolyte solutions were purged with N₂ for at least 10 min prior to measurements.

EIS measurements were performed at the open circuit potential with a sinusoidal voltage perturbation amplitude of 10 mV in the frequency range from 1×10^{-1} to 1×10^{5} Hz. The Nyquist plots obtained were fitted by a Randles equivalent circuit to estimate the charge transfer resistance ($R_{\rm ct}$). This circuit consists of a resistance element corresponding to the bulk solution in series with a parallel combination of an element of constant phase and Faradaic impedance, which is related to $R_{\rm ct}$ and Warburg impedance representing the interfacial electron transfer resistance and the diffusion of the redox

Scheme 3. Two Different Sequences of Surface Modification Used in This Study to Prepare Bifunctionalized Copolymer Layers^a



Bifunctionalized surface

^aSequence A: Amine groups (step 1) then thiol groups (step 2) of the copolymer layer are modified. Sequence B: thiol groups (step 1') then amine groups (step 2') are modified.

probe in solution, respectively.⁴⁵ $R_{\rm ct}$ can also be obtained from the diameter of the high frequency semicircle.⁴⁶ The variation of $R_{\rm ct}$ can be related to the gold surface coverage by the following equation.⁴⁷

surface coverage =
$$1 - \frac{R_{ct}^{0}}{R_{ct}}$$
 (1)

where R_{ct}^{0} and R_{ct} correspond to the charge transfer of the bare gold surface and the modified surface, respectively.

Atomic Force Microscopy (AFM). AFM images were recorded in TappingTM mode (in light tapping regime) with a Bruker Nanoscope V device equipped with a PPP NCHR Nano Sensor tip. They were then analyzed using Nanoscope Analysis 1.8 software (Bruker). Briefly, recorded images were flattened by a first order polynomial to remove the tilt. The average roughness of the recorded images was evaluated from $5 \times 5 \ \mu\text{m}^2$ images.

Water Contact Angle Measurements. Static water contact angle measurements were carried out at room temperature with an OCA-20 apparatus (DataPhysics Instruments GmbH, Germany) in the sessile drop configuration. A drop (5 μ L) of Milli-Q water was deposited onto the surface and the recorded image was analyzed by the SCA 20

software to determine the contact angle. At least two measurements were performed at different locations on the surface.

Elliposmetry Measurements. Film thickness was estimated by performing ellipsometry measurements as a function of incidence angle, at a constant wavelength of 658 nm on an accurion nanofilm EP4 ellipsometer. Because of the roughness of both the gold/film and film/air interfaces, combined with the uncertainty on the index of refraction of the film and gold, ellipsometry can only provide approximate values for film thickness. Therefore, the Drude approximation, which is valid for very thin films, was used. This approximation is a series development limited to first order of the ellipsometric angles (Delta and Psy) versus thickness, with the ellipsometric angles of the bare substrate used as reference point. We simulated the ellipsometric angles using tabulated values for gold and an index of refraction of 1.5 for the film, and found that, for our largest incidence angle (80°) , the linearity between film thickness and Delta is respected up to 5 nm thickness. For our lowest incidence angle (40°) , the linearity is valid over a larger range of film thicknesses, up to about 25 nm. Therefore, we limited our analysis to incidence angles comprised between 40 and 50°. We then used Drude's equations⁴⁸ to compute film thickness based on the ellipsometry data.

Table	1. Atomic	Percentages	of Gold,	Nitrogen	and Sul	ur Measure	d by XP	S for G	old Surfaces	Modified	with P(DM	A-co-
TlaAm) Layers P	Prepared in I	Different	Condition	S							

conditions used for the preparation of	the copolymer layer		S				
copolymer concentration $(mg \cdot mL^{-1})$	amine derivative	S-Au ^a (%)	$S-C + S-H^{a}(\%)$	S_{tot}^{a} (%)	$(S-C + SH)/S_{tot}^{a}$	N (%)	Au (%)
0.2	ethylenediamine	0.8	2.0	2.8	0.71	10.1	13.9
2	ethylenediamine	0.4	2.4	2.8	0.86	12.5	0.2
2	ethanolamine	1.2	1.0	2.2	0.45	7.8	20.3
^a S-Au corresponds to the thiol grou	ps anchored on the	gold surface, S	-C and S-H corres	pond to the	thiol groups that are	not ancho	red to the

gold surface, and S_{tot} corresponds to the total amount of thiol groups in the copolymer layer.

Epifluorescence Microscopy. The copolymer layers grafted with the fluorescent Rhod B-PEG-SH or RGD-FITC derivatives were observed with an optical inverted epifluorescence IX71 microscope (Olympus, Japan) equipped with a CCD camera, a fluorescence illuminator and various filter units. Images were recorded at 10× magnification and processed using the Cell Sens Dimension 1.7 software (Olympus, Japan). Scratches was deliberately made on the modified surfaces to compare the fluorescence resulting from the grafted copolymer layer with the background. Images were then analyzed with *IGOR Pro* software (version 6.22A, Wavemetrics, Inc.) according to the procedure described before¹² to evaluate the fluorescence intensity.

High Performance Liquid Chromatography-Mass Spectrometry (HPLC-MS). A LC system by ThermoFisher Products (San Jose, CA, U.S.A.) equipped with an Accela 1250 pump and an Accela Autosampler, was used to quantify the amount of OVA peptide released from copolymer layers under DTT treatment. For this purpose, surfaces modified with a copolymer layer grafted with OVA peptide were put in contact with 1 mL of reductive DTT solution (2 mM of DTT in 10 mM HEPES, pH 7.2). This solution was further collected to determine the amount of released compound by HPLC-MS. Briefly, separation of OVA peptide was performed on a C18 Alltima column using a linear gradient from 97% of solution A (H₂O, 1% CH₃CN, and 0.1% HCOOH) and 3% of solution B (CH₃CN) for 3 min to 10% solution A and 90% of solution B for 28 min. The flow rate was 0.2 mL·min⁻¹ and the column temperature was kept at 30 °C. Before penetrating into the column, the sample was kept at 7 °C. The recording of the mass spectra were performed online, on the collected fractions using an Orbitrap mass spectrometer (ThermoFisher, San Jose, CA) equipped with an ESI source in positive mode. The following ESI inlet conditions were used for the analysis: the capillary temperature was set to 380 °C, the pressure of the sheath gas to 47 PSI and the pressure of the auxiliary gas to 20 PSI. Mass spectra were recorded by using the doubly charged selected ion monitoring (DC-SIM) mode of the doubly charged ion peak 533.78 with a collision energy (CE) of 10%.

RESULTS AND DISCUSSION

Influence of the Conditions Used for the Preparation of the Copolymer Layers on Their Structure. To prepare bifunctional copolymer layers presenting both free amino and thiol groups for subsequent functionalization, the P(DMA-co-TlaAm) copolymer was put in contact with gold surfaces in the presence of ethylenediamine. According to the reaction described in Scheme 2, the nucleophilic diamine derivative reacts with the thiolactone groups of the copolymer to form both thiol and amino pendant groups along the macromolecular chain. While a part of the released thiol groups is involved in the anchorage of the copolymer chains onto the gold surface, the remaining -SH groups are available, as well as the amino groups, to further immobilize compounds of interest onto the copolymer layer. However, a possible side reaction between two thiolactone groups and one diamine molecule, leading to the formation of cross-links between the copolymer chains, can also occur, as illustrated in Scheme S1. For this reason, the formation of the copolymer layer was investigated at two different concentrations, namely, 0.2 and 2 mg·mL⁻¹. First, to confirm the presence of the copolymer layer, static contact angle measurements were performed on flat gold surfaces before and after treatment by the copolymer and the diamine. The contact angle decreased from ~71° to ~45° and ~50° upon treatment with a copolymer concentration of 0.2 and 2 mg·mL⁻¹, respectively, in agreement with the hydrophilic nature of introduced ethylenediamine residues.

The obtained surfaces were then analyzed by XPS to assess the influence of the copolymer concentration on their chemical composition. A surface modified with the P(DMA-*co*-TlaAm) copolymer in the presence of ethanolamine (i.e., monoamine) was also characterized for the comparison (Table 1).

The survey scans of all the samples showed Au, C, N, O, and S atoms as expected from their composition (as illustrated in Figure S1A for one sample, Supporting Information). These results confirm the attachment of the aminolyzed copolymer chains onto the gold surface. Moreover, the XPS spectra measured with high energy resolution in the $S_{\rm 2p}$ region can be decomposed in two peaks centered on ~161.5 and ~164 eV and corresponding to sulfur atoms anchored (S-Au) or not (S-H and S-C) to the gold surface, respectively. The quantifications performed on the sulfur, nitrogen, and gold peaks measured for copolymer layers grafted in the presence of ethylenediamine (Table 1), showed that a higher concentration of copolymer resulted in a higher nitrogen content, a much lower percentage of gold and a relative higher ratio of unbound sulfur atoms $((S-H + S-C)/S_{tot})$, while the total amount of sulfur (S_{tot}) remained unchanged. Interestingly, the comparison with a sample prepared with the same concentration of copolymer (i.e., 2 mg·mL⁻¹), but in the presence of ethanolamine, showed a lower attenuation of the gold signal. Altogether, these results suggest that thicker copolymer layers were grafted onto gold surfaces when the reaction was performed in the presence of diamine, in contrast with the formation of a monolayer when a monoamine was used.

To check this point, film thickness prepared in the presence of ethylenediamine was estimated by performing ellipsometry measurements. For the film prepared at a copolymer concentration of 0.2 mg/mL, an average film thickness of 3.6 nm was found, when using an index of refraction of 1.5 for the film. If the index of refraction of the film is decreased to 1.4 (an improbably low value), the film thickness increases to 4.1 nm. For the sample prepared at 2 mg/mL, the average film thickness is 26.5 nm for an index of refraction of 1.5, and 30.1 nm for an index of refraction of 1.4. This is slightly above the limit for linearity, and is thus likely slightly underestimated. Nevertheless, the average film thickness increases by a factor of about 7.5 upon increasing the copolymer concentration by a factor of 10 which, considering the approximations used, is reasonable. Summing up, the film thickness is about 4 nm for 0.2 mg/mL, and about 30 nm for 2 mg/mL.

Samples prepared in different conditions were also analyzed

by AFM (Figure 1). The surfaces prepared using copolymer

Figure 1. AFM images $(5 \times 5 \ \mu m^2)$ of gold surfaces modified with copolymer layers prepared in different conditions: with a 2 mg·mL⁻¹ copolymer solution in the presence of ethanolamine (A); with 2 mg·mL⁻¹ (B) and 0.2 mg·mL⁻¹ (C) copolymer solutions in the presence of ethylenediamine. Insets show 0.5 × 0.5 μm^2 zoom-in images.

and ethanolamine showed a morphology close to the bare gold surface (Figure 1A). The average roughness of bare gold and

gold surface covered with a copolymer grafted in the presence of ethanolamine was 1.1 ± 0.1 and 1.4 ± 0.1 nm, respectively. The unchanged morphology and the similar roughness attest for the deposition of a thin monolayer of copolymer onto gold surface in the presence of ethanolamine. By contrast, the surfaces prepared in the presence of ethylenediamine showed copolymer aggregates whose size increased with the copolymer concentration (Figure 1B,C).

The average roughness measured for the surfaces prepared with 0.2 and 2 mg·mL⁻¹ copolymer solutions is 1.4 ± 0.1 and 2.1 \pm 0.6 nm, respectively. The roughness of the surface prepared with the lower copolymer concentration is similar to the one measured for surfaces functionalized in the presence of ethanolamine. Therefore, these results confirmed that the copolymer layers prepared in the presence of diamine are composed of aggregates that come from the side cross-linking reaction occurring during the aminolysis process, between the diamine derivative and the thiolactone rings of the copolymer, especially when a higher concentration of copolymer is used.

Modification of the Pendent Amine Groups of the Copolymer Layers. The modification of the free amino groups present in the copolymer layers prepared with ethylenediamine was tested by using two different carboxylic acid derivatives (Scheme 3, modification sequence A, step 1). First a fluorescent bioadhesive peptide (RGD-FITC) preactivated by EDC/sulfo-NHS, was put in contact with the copolymer layer. Two different copolymer layers prepared with 0.2 and 2 mg·mL⁻¹ copolymer solutions were used for this test. The inspection of the resulting surfaces by fluorescence microscopy evidenced the presence of the FITC-labeled peptide on both samples but also heterogeneities that are larger and more fluorescent on the sample prepared with a higher copolymer concentration (Figure 2).

Similar tests performed with nonpreactivated RGD-FITC peptide did not provide fluorescence (result not shown). Therefore, it can be concluded that the fluorescence signal observed after addition of the preactivated peptide onto the modified surfaces was due to the covalent grafting of the peptide molecules on the free amino groups of the copolymer layer and not to the adsorption of the peptide molecules on the copolymer layer or on the gold surface. The heterogenities observed on the grafed surfaces result from the intrinsic agregated structure of the copolymer layers, as evidenced by AFM at a smaller scale (Figure 1). Moreover, the higher



Figure 2. Fluorescence images of gold surfaces modified with a copolymer layer prepared in the presence of ethylenediamine then grafted with a RGD-FITC peptide: copolymer layer prepared using 2 (A) and 0.2 mg·mL⁻¹ (B) copolymer solutions. The exposition time used to record the images was 1 and 5 s for images (A) and (B), respectively. A deliberate scratch (black line, indicated by a white arrow) was made on each surface to show the fluorescence difference between the uncovered background and the grafted layer.



Figure 3. (A–C) Nyquist plots traced from EIS measurements. (B–D) R_{ct} and surface coverage values estimated after each surface treatment, by fitting the values of the Nyquist plot with a Randles equivalent circuit. Measurements were performed on bare gold electrode (reference surface) (1), then on electrode modified with a copolymer layer formed in the presence of ethylenediamine (2), subsequently treated with PEG-SH in the presence of CaT (3), and finally exposed to a reducing medium (4), which is DTT (A, B) or L-glutathione (C, D).

fluorescence intensity observed for the surface modified with a more concentrated copolymer solution, is in agreement with the presence of larger copolymer aggregates rich in free amino groups (Figure 1 and Table 1).

To evaluate more quantitatively the amount of carboxylic acid derivative that can be grafted on the copolymer layers, trifluorobutyric acid molecules containing fluorine atoms easily detected by XPS, were grafted on a copolymer layer via the EDC/sulfo-NHS coupling. This test was performed only on a thick copolymer layer prepared with a 2 mg·mL⁻¹ copolymer solution. Indeed, in these conditions, the gold substrate is only poorly seen by XPS (Table 1), so that the measured signals essentially relates to the bulk composition of the modified copolymer layer. XPS measurements performed on this layer (Supporting Information, Figure S1B) revealed the presence of an additional fluorine signal as expected. To estimate the grafting degree on the amino groups of the copolymer layer, XPS spectra were recorded with high energy resolution in the S_{2p} and F_{1s} regions. It was determined from these measurements that about 23 trifluorobutyric acid molecules were grafted for 100 thiolactone units. While this grafting degree is quite limited, it is worth noting that a part of the amino groups released during the grafting of the copolymer layer on gold surface were involved in cross-links due to the side reaction occurring at the same time. Therefore, the amount of free amino groups effectively present in the copolymer layers and available for the immobilization of a carboxylic derivative, is lower than expected when considering the composition of the copolymer.

the presence of amine groups in the copolymer layers, the free thiol groups distributed along the copolymer chains, offer the possibility to reversibly graft thiolated compounds through a disulfide link. Indeed, such a link can be easily cleaved under mild reductive conditions to release the grafted compound on demand. To test this approach, the grafting and the subsequent release of PEG-SH (used as a model thiolated molecule) on the copolymer layers was studied. For this, thicker layers prepared with a 2 mg·mL⁻¹ copolymer in the presence of ethylenediamine, were first exposed to a PEG-SH solution in the presence of CaT, to get oxidative conditions required for the formation of the disulfide link. In a second step, the modified surfaces were immersed in a reducing medium to operate the release of the PEG-SH molecules through the cleavage of disulfide bonds between the thiol groups of the copolymer and the PEG-SH model molecules. Two different reducing solutions containing DTT or L-glutathione were tested for this last step. Impedance measurements were performed after each step to detect changes at the Au-solution interface. The R_{ct} values were computed by modeling the Nyquist plots with a Randles equivalent circuit and an estimation of the coverage of the surface, directly related to $R_{ct'}$ was also calculated (eq 1). Nyquist plots as well as the R_{ct} and surface coverage values measured after each surface treatment are displayed in Figure 3. The comparison of Nyquist plots obtained for a gold surface modified by the copolymer (Figure 3, curves 2) and the same surface treated by a PEG-SH solution in oxidizing condition (Figure 3, curves 3) evidenced the grafting of PEG molecules

Grafting and Release of a Thiolated Compound on

the Free Thiol Groups of the Copolymer Layers. Besides

on the copolymer layer. As a result, significant increases of R_{ct} (from 40 to 104 k Ω in Figure 3B and from 18 to 69 k Ω Figure 3D) and surface coverage (Figure 3B,D) are observed. Altogether these results prove the successful grafting of PEG-SH molecules on the copolymer layer,⁴⁴ as well as the stability of the copolymer layer when exposed to an oxidizing agent, such as CaT. In contrast, significant decreases of R_{ct} (decrease of 46 and 20 k Ω in Figure 3B and D, respectively) and surface coverage were observed when the surfaces were immersed in reducing solutions of DTT (Figure 3B) or L-glutathione (Figure 3D). These results demonstrate, on one hand, the stability of the copolymer layer when exposed to both types of reducing agents (after surface treatment with either DTT or Lglutathione, the R_{ct} and surface coverage values did not come back to values corresponding to bare gold) and, on the other hand, prove the successful release of PEG-SH molecules from the copolymer layers due to the cleavage of disulfide links. However, the release of thiolated compound was more pronounced when the surfaces were exposed to DTT (see difference between curves 3 and 4 in Figure 3A) compared to Lglutathione (see difference between curves 3 and 4 in Figure 3C), even if the DTT concentration (2 mM) used for these tests was much lower than the L-glutathione one (10 mM). The stronger ability of DTT to cleave disulfide links compared to Lglutathione is explained by its stronger reducing power.⁴

Though the release of PEG-SH was not fully achieved when using both reducing agents (the EIS response measured after the reducing treatment could not superpose with the initial EIS response measured prior to PEG-SH grafting; see the nonsuperposition of curves 2 and 4 in Figure 3A,C), the fact that a large part of thiolated compound could be released in the presence of a biocompatible reducing agent (i.e., L-glutathione) is promising for potential biological applications of these layers. While the general grafting/release of the thiolated PEG under redox stimulation was clearly evidenced (Figure 3), it is worth noting that a large variation of absolute R_{ct} values was observed from sample to sample after grafting the copolymer layer onto the gold surface (see difference of R_{ct} values displayed in Figure 3B,D for surface treatment 2) and, consequently, after grafting the thiolated compound (see difference of R_{ct} values displayed in Figure 3B,D for surface treatment 3). This variation between the samples can be attributed to two phenomena. First, the uncontrolled cross-linking reaction occurring during the aminolysis process in the presence of the diamine results in a poor control of the amount of polymer immobilized onto the gold surface. Indeed, the size of the cross-linked copolymer aggregates grafted onto the surface slightly varied from sample to sample resulting in variation of EIS response. Second, copolymer layers prepared in the presence of a diamine present positively charged amino groups (-NH₃⁺), while neutral layers were obtained when using ethanolamine.⁴⁴ Yet, the R_{ct} values not only depend on the alteration of the resistance generated by the grafting (or release) of passivating compounds on the surface but, also on the presence of ionic charges on the surface, which can interfere with the negatively charged redox probe.^{46,50} So, in the present study, the EIS results qualitatively proved the successful grafting and release of the PEG-SH compound but did not allow for quantitative analysis.

Sequential Modification of Amine and Thiol Groups Present in the Copolymer Layers. After having evidenced the possibility to modify separately amine and thiol groups present in the copolymer layers, we studied the successive modification of both chemical groups to prepare bifunctionalized layers showing redox-responsive properties. For this purpose, two different sequences of modification of the copolymer layers were tested (Scheme 3): the amino groups were modified first and subsequently the thiol groups (sequence A) or the reverse (sequence B). To estimate the influence of the grafting sequence on the amount of thiolated derivative immobilized on free thiol groups of the copolymer layer, fluorescent Rhod B-PEG-SH was used. The images recorded by epifluorescence microscopy for copolymer layers bifunctionalized with glycylglycine and Rhod B-PEG-SH according to the sequences A and B (Scheme 3) were analyzed and the relative fluorescence intensities measured for these surfaces are shown in Figure 4. The value obtained for a



Figure 4. Relative fluorescence intensity measured for bifunctionalized copolymer layers prepared with a 2 mg/mL copolymer solution in the presence of ethylenediamine, which have then be grafted with Rhod B-PEG-SH and glycylglycine, according to the grafting sequence A or B described in the Scheme 3. The average intensity value measured for a copolymer layer modified only with Rhod B-PEG-SH (Seq B, step 1') was added for comparison.

copolymer layer modified with Rhod B-PEG-SH only was also added for comparison. Both bifunctionalized layers showed fluorescence of similar intensity, demonstrating the successful grafting of Rhod B-PEG-SH, regardless of the modification sequence (A or B). However, the fluorescence intensity measured on these bifunctionalized surfaces was divided by a factor of 2 compared to the monofunctionalized copolymer layer grafted with Rhod B-PEG-SH only. This indicates that the EDC/sulfo-NHS treatment performed to graft glycylglycine on amino groups of the copolymer layer impacted the grafting of the thiolated derivative on the thiol groups, independently of the grafting sequence used. It seems that this chemical treatment most likely deactivated a part of free thiol groups present in the copolymer layer during the first step (Scheme 3, step 1) of the grafting sequence A but also cleaved some disulfide links formed during the first step (Scheme 3, step 1') of the grafting sequence B.

The preparation of a bifunctionalized copolymer layer according to the grafting sequence A was followed by EIS (Figure 5). The Nyquist plots revealed a clear increase of R_{ct} (from 49 to 110 k Ω) and surface coverage after the grafting of PEG-SH on free thiol groups of a copolymer layer premodified with glycylglycine (Figure 5B). This result is in agreement with epifluorescence microscopy measurements (Figure 4), showing that some free thiol groups were still available in the copolymer layer after the modification of the amine groups and could be successfully used to immobilize a thiolated derivative. More-



Figure 5. (A) Nyquist plots of EIS. (B) R_{ct} and surface coverage values estimated after each surface treatment, by fitting the values of the Nyquist plot with a Randles equivalent circuit. Measurements were performed on bare gold electrode (reference surface) (1), then on the same electrode modified with a copolymer layer formed in the presence of ethylenediamine and grafted with glycylglycine on amino groups according to the sequence A described in the Scheme 3 (2), subsequently treated with PEG-SH in the presence of CaT (3), and finally exposed to DTT (4).

over, the treatment of such a bifunctionalized surface by DTT (Figure 5, surface treatment 4) or L-glutathione (results not shown) induced a strong decrease of R_{ct} due to the release of PEG-SH molecules. Altogether, the EIS experiments prove that bifunctionalized layers show redox-responsive properties, allowing the release of a compound of interest in demand.

Next, to quantify the ability of bifunctionalized copolymer layers to release a compound of interest under redox stimulation, an OVA peptide incorporating a cysteine unit and used as a model molecule, was grafted on free thiol groups of a copolymer layer premodified with glycylglycine (Scheme 3, sequence A, step 2). The resulting surface was treated by DTT and the composition of the supernatant was characterized by HPLC-MS. It was measured that 0.02 ± 0.01 ng of OVA peptide was released per mm² of treated surface, which corresponds to 0.011 ± 0.006 molecules per nm². A high variability (of about 50%) was observed, demonstrating by other means than EIS, that the amount of copolymer grafted on the gold surface is poorly reproducible from one surface to another one, because of the cross-linking reaction occurring during the preparation of the copolymer layer. A similar test was performed by grafting then releasing OVA peptide on a non premodified copolymer layer prepared in the presence of ethylenediamine (Scheme 3, sequence B, step 1'). A value of 0.025 ± 0.001 molecules per nm² was obtained. These results are in agreement with the epifluorescence microscopy quantifications displayed in Figure 3, which evidenced that a higher amount of thiolated compound is immobilized on a copolymer layer whose amine groups are not grafted compared to a premodified layer. For comparison, Deschaume et al. prepared SAMs of amine-terminated silanes to graft different peptides and proteins.⁵¹ Among others, a RGD peptide with 7 amino acids was grafted on these surfaces via a 3-succinimidyl-3-maleimidopropionate linker, and a density of 0.42 molecules per nm was obtained. The higher value of peptide density observed in this study compared to our case, may be due to the fact that SAMs layers present a much higher amount of functional groups per surface unit compared to the copolymer layer used in our approach. The bifunctionalized layers developed in this study could therefore be used for applications in which the compound of interest does not need to be grafted with a high surface density, such as enzyme-functionalized surfaces used in biocatalysis, for instance.

CONCLUSION

Thin macromolecular layers containing both free amine and thiol groups were successfully grafted on gold surfaces in a onestep procedure using a thiolactone-based copolymer as stable precursor. The obtained layers were further bifunctionalized through reactions of their free amine and thiol groups with carboxylic acid and thiolated derivatives, respectively. Finally, the release of thiolated derivatives immobilized on these macromolecular layers through disulfide bond cleavage under mild reducing conditions was demonstrated, proving the redoxresponsiveness of these layers. Such bifunctional layers can be advantageously developed to produce bioactive surfaces presenting two active components at the same time, such as enzyme and substrate or bioadhesive peptide and growth factor or antibacterial peptide. Moreover, the possibility to release one of the components on demand, under biocompatible conditions, offers the opportunity to control biological processes such as an enzymatic reaction or a cellular mechanism such as differentiation or apoptosis for animal cells or cellular killing for microorganisms.

ASSOCIATED CONTENT

S Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acs.lang-muir.8b00525.

XPS survey scan measured for a copolymer layer prepared in the presence of diamine on gold substrate and grafted with trifluorobutyric acid (Figure S1). Schematic representation of the possible competing side reaction between two thiolactone groups and one diamine molecule, leading to the formation of cross-links between the copolymer chains (Scheme S1; PDF).

AUTHOR INFORMATION

Corresponding Authors

*E-mail: sophie.demoustier@uclouvain.be. *E-mail: karine.glinel@uclouvain.be.

ORCID 💿

Filip E. Du Prez: 0000-0001-7727-4155 Sophie Demoustier-Champagne: 0000-0003-3045-6060

Langmuir

Present Address

[§]Université Paris Est, ICMPE (UMR7182), CNRS, UPEC, F-94320 Thiais, France.

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work was supported by the Belgian Federal Science Policy (IAP Program P7/05). Pierre Eloy and Cécile d'Haese are thanked for their help with XPS and AFM measurements. Diana Ramirez and Raoul Rozenberg are acknowledged for their help with HPLC-MS measurements. Alain Jonas and Delphine Magnin are thanked for their technical assistance with ellipsometry measurements. C.C. benefits from a FRIA research fellowship provided by the F.R.S.-FNRS. K.G. is a Research Associate of the F.R.S.-FNRS.

REFERENCES

(1) Love, J. C.; Estroff, L. A.; Kriebel, J. K.; Nuzzo, R. G.; Whitesides, G. M. Self-Assembled Monolayers of Thiolates on Metals as a Form of Nanotechnology. *Chem. Rev.* **2005**, *105*, 1103–1169.

(2) Draper, M. C.; Crick, C. R.; Orlickaite, V.; Turek, V. A.; Parkin, I. P.; Edel, J. B. Superhydrophobic Surfaces as an On-Chip Microfluidic Toolkit for Total Droplet Control. *Anal. Chem.* **2013**, *85*, 5405–5410.

(3) Wildling, L.; Unterauer, B.; Zhu, R.; Rupprecht, A.; Haselgrübler, T.; Rankl, C.; Ebner, A.; Vater, D.; Pollheimer, P.; Pohl, E. E.; Hinterdorfer, P.; Gruber, H. J. Linking of sensor molecules with amino groups to amino-functionalized AFM tips. *Bioconjugate Chem.* **2011**, *22*, 1239–1248.

(4) Barbosa, O.; Torres, R.; Ortiz, C.; Berenguer-Murcia, Á.; Rodrigues, R. C.; Fernandez-Lafuente, R. Heterofunctional supports in enzyme immobilization: From traditional immobilization protocols to opportunities in tuning enzyme properties. *Biomacromolecules* **2013**, *14*, 2433–2462.

(5) Gray, C. J.; Weissenborn, M. J.; Eyers, C. E.; Flitsch, S. L. Enzymatic reactions on immobilised substrates. *Chem. Soc. Rev.* 2013, 42, 6378–6405.

(6) Fernandes, A. E.; Riant, O.; Jonas, A. M.; Jensen, K. F. One "Click" to controlled bifunctional supported catalysts for the Cu/ TEMPO-catalyzed aerobic oxidation of alcohols. *RSC Adv.* **2016**, *6*, 36602–36605.

(7) Min, K.; Yoo, Y. J. Recent progress in nanobiocatalysis for enzyme immobilization and its application. *Biotechnol. Bioprocess Eng.* **2014**, *19*, 553–567.

(8) Hersel, U.; Dahmen, C.; Kessler, H. RGD modified polymers: Biomaterials for stimulated cell adhesion and beyond. *Biomaterials* **2003**, *24*, 4385–4415.

(9) Perlin, L.; MacNeil, S.; Rimmer, S. Production and performance of biomaterials containing RGD peptides. *Soft Matter* **2008**, *4*, 2331–2349.

(10) Zouani, O. F.; Chollet, C.; Guillotin, B.; Durrieu, M. C. Differentiation of pre-osteoblast cells on poly(ethylene terephthalate) grafted with RGD and/or BMPs mimetic peptides. *Biomaterials* **2010**, *31*, 8245–8253.

(11) Yu, Q.; Wu, Z.; Chen, H. Dual-function antibacterial surfaces for biomedical applications. *Acta Biomater.* **2015**, *16*, 1–13.

(12) Glinel, K.; Jonas, A. M.; Jouenne, T.; Galas, L.; Huck, W. T. S. Antibacterial and Antifouling Polymer Brushes Incorporating Antimicrobial Peptide. *Bioconjugate Chem.* **2009**, *20*, 71–77.

(13) Thebault, P.; Taffin de Givenchy, E.; Guittard, F.; Guimon, C.; Géribaldi, S. Self-assembled monolayers of semi-fluorinated thiols and disulfides with a potentially antibacterial terminal fragment on gold surfaces. *Thin Solid Films* **2008**, *516*, 1765–1772.

(14) Carvalho, A. L.; Vale, A. C.; Sousa, M. P.; Barbosa, A. M.; Torrado, E.; Mano, J. F. Antibacterial bioadhesive layer-by-layer coatings for orthopedic applications. *J. Mater. Chem. B* **2016**, *4*, 5385– 5393.

(15) Palchesko, R. N.; Buckholtz, G. A.; Romeo, J. D.; Gawalt, E. S. Co-immobilization of active antibiotics and cell adhesion peptides on calcium based biomaterials. *Mater. Sci. Eng., C* 2014, *40*, 398–406.

(16) Godjevargova, T.; Dayal, R.; Marinov, I. Simultaneous covalent immobilization of glucose oxidase and catalase onto chemically modified acrylonitrile copolymer membranes. *J. Appl. Polym. Sci.* **2004**, *91*, 4057–4063.

(17) Fernandes, A. E.; Riant, O.; Jensen, K. F.; Jonas, A. M. Molecular Engineering of Trifunctional Supported Catalysts for the Aerobic Oxidation of Alcohols. *Angew. Chem., Int. Ed.* **2016**, *55*, 11044–11048.

(18) Goddard, J. M.; Hotchkiss, J. H. Polymer surface modification for the attachment of bioactive compounds. *Prog. Polym. Sci.* 2007, *32*, 698–725.

(19) Ferretti, S.; Paynter, S.; Russell, D. A.; Sapsford, K. E.; Richardson, D. J. Self-assembled monolayers: a versatile tool for the formulation of bio-surfaces. *TrAC, Trends Anal. Chem.* **2000**, *19*, 530–540.

(20) Wong, L. S.; Khan, F.; Micklefield, J. Selective covalent protein immobilization: Strategies and applications. *Chem. Rev.* **2009**, *109*, 4025–4053.

(21) Gooding, J. J.; Ciampi, S. The molecular level modification of surfaces: from self-assembled monolayers to complex molecular assemblies. *Chem. Soc. Rev.* **2011**, *40*, 2704–2718.

(22) Mahapatro, A. Bio-functional nano-coatings on metallic biomaterials. *Mater. Sci. Eng.*, C 2015, 55, 227–251.

(23) Kind, M.; Wöll, C. Organic surfaces exposed by self-assembled organothiol monolayers: Preparation, characterization, and application. *Prog. Surf. Sci.* **2009**, *84*, 230–278.

(24) Feng, J.; Xu, G. H.; An, Y.; Zeng, X. Construction of the homogeneously mixed SAM composed of octyltriethoxysilane and octadecyltrichlorosilane by taking advantage of the molecular steric restriction. *Colloids Surf.*, A **2008**, 316, 194–201.

(25) Folkers, J. P.; Laibinis, P. E.; Whitesides, G. M. Self-assembled monolayers of alkanethiols on gold: the adsorption and wetting properties of monolayers derived from two components with alkane chains of different lengths. *J. Adhes. Sci. Technol.* **1992**, *6*, 1397–1410.

(26) Laibinis, P. E.; Nuzzo, R. G.; Whitesides, G. M. Structure of monolayers formed by coadsorption of two n-alkanethiols of different chain lengths on gold and its relation to wetting. *J. Phys. Chem.* 1992, 96, 5097–5105.

(27) Mani, G.; Johnson, D. M.; Marton, D.; Feldman, M. D.; Patel, D.; Ayon, A. A.; Agrawal, C. M. Drug delivery from gold and titanium surfaces using self-assembled monolayers. *Biomaterials* **2008**, *29*, 4561–4573.

(28) Das, M.; Shim, K. H.; An, S. S. A.; Yi, D. K. Review on gold nanoparticles and their applications. *J. Toxicol. Environ. Health Sci.* **2011**, *3*, 193–205.

(29) Dijksma, M.; Kamp, B.; Hoogvliet, J. C.; Van Bennekom, W. P. Formation and electrochemical characterization of self-assembled monolayers of thioctic acid on polycrystalline gold electrodes in phosphate buffer pH 7.4. *Langmuir* **2000**, *16*, 3852–3857.

(30) Mrksich, M.; Whitesides, G. M. Patterning self-assembled monolayers using microcontact printing: A new technology for biosensors? *Trends Biotechnol.* **1995**, *13*, 228–235.

(31) Srisombat, L.; Jamison, A. C.; Lee, T. R. Stability: A key issue for self-assembled monolayers on gold as thin-film coatings and nanoparticle protectants. *Colloids Surf.*, A **2011**, 390, 1–19.

(32) Rouhana, L. L.; Moussallem, M. D.; Schlenoff, J. B. Adsorption of short-chain thiols and disulfides onto gold under defined mass transport conditions: coverage, kinetics, and mechanism. *J. Am. Chem. Soc.* **2011**, *133*, 16080–16091.

(33) Vericat, C.; Vela, M. E.; Salvarezza, R. C. Self-assembled monolayers of alkanethiols on Au (111): surface structures, defects and dynamics. *Phys. Chem. Chem. Phys.* **2005**, *7*, 3258–3268.

(34) Farah, A. A.; Zheng, S. H.; Morin, S.; Bensebaa, F.; Pietro, W. J. Thiolated poly(ε -caprolactone) macroligand with vacant coordination sites on gold substrate: Synthesis and surface characterization. *Surf. Sci.* **2007**, *601*, 1677–1683.

(35) Le Neindre, M.; Nicolaÿ, R. Polythiol copolymers with precise architectures: a platform for functional materials. *Polym. Chem.* **2014**, *5*, 4601–4611.

(36) Stamenovic, M. M.; Espeel, P.; Baba, E.; Yamamoto, T.; Tezuka, Y.; Du Prez, F. E. Straightforward synthesis of functionalized cyclic polymers in high yield via RAFT and thiolactone-disulfide chemistry. *Polym. Chem.* **2013**, *4*, 184–193.

(37) Reinicke, S.; Espeel, P.; Stamenović, M. M.; Du Prez, F. E. One-Pot Double Modification of p(NIPAAm): A Tool for Designing Tailor-Made Multiresponsive Polymers. *ACS Macro Lett.* **2013**, *2*, 539–543.

(38) Espeel, P.; Goethals, F.; Du Prez, F. E. One-Pot Multistep Reactions Based on Thiolactones: Extending the Realm of Thiol–Ene Chemistry in Polymer Synthesis. *J. Am. Chem. Soc.* **2011**, *133*, 1678– 1681.

(39) Reinicke, S.; Espeel, P.; Stamenović, M. M.; Du Prez, F. E. Synthesis of multi-functionalized hydrogels by a thiolactone-based synthetic protocol. *Polym. Chem.* **2014**, *5*, 5461–5470.

(40) Espeel, P.; Goethals, F.; Stamenovic, M. M.; Petton, L.; Du Prez, F. E. Double modular modification of thiolactone-containing polymers: towards polythiols and derived structures. *Polym. Chem.* **2012**, *3*, 1007–1015.

(41) Espeel, P.; Du Prez, F. E. One-pot multi-step reactions based on thiolactone chemistry: A powerful synthetic tool in polymer science. *Eur. Polym. J.* **2015**, *62*, 247–272.

(42) Goethals, F.; Frank, D.; Du Prez, F. E. Protected thiol strategies in macromolecular design. *Prog. Polym. Sci.* 2017, 64, 76–113.

(43) Reinicke, S.; Rees, H. C.; Espeel, P.; Vanparijs, N.; Bisterfeld, C.; Dick, M.; Rosencrantz, R. R.; Brezesinski, G.; de Geest, B. G.; Du Prez, F. E.; Pietruszka, J.; Böker, A. Immobilization of 2-Deoxy-D-ribose-5phosphate Aldolase in Polymeric Thin Films via the Langmuir-Schaefer Technique. ACS Appl. Mater. Interfaces **2017**, *9*, 8317–8326.

(44) Belbekhouche, S.; Reinicke, S.; Espeel, P.; Du Prez, F. E.; Dupont-Gillain, C.; Jonas, A. M.; Demoustier-Champagne, S.; Glinel, K. Polythiolactone-based redox-responsive layers for the reversible release of functional molecules. *ACS Appl. Mater. Interfaces* **2014**, *6*, 22457–22466.

(45) K'Owino, I. O.; Sadik, O. A. Impedance Spectroscopy: A Powerful Tool for Rapid Biomolecular Screening and Cell Culture Monitoring. *Electroanalysis* **2005**, *17*, 2101–2113.

(46) Wallen, R.; Gokarn, N.; Bercea, P.; Grzincic, E.; Bandyopadhyay, K. Mediated Electron Transfer at Vertically Aligned Single-Walled Carbon Nanotube Electrodes During Detection of DNA Hybridization. *Nanoscale Res. Lett.* **2015**, *10*, 268–278.

(47) Ribaut, C.; Reybier, K.; Torbiero, B.; Launay, J.; Valentin, A.; Reynes, O.; Fabre, P. L.; Nepveu, F. Strategy of red blood cells immobilisation onto a gold electrode: Characterization by electrochemical impedance spectroscopy and quartz crystal microbalance. *IRBM* **2008**, *29*, 141–148.

(48) Tompkins, H. G. A User's Guide to Ellipsometry; Academic Press: Boston, 1993.

(49) Rothwarf, D. M.; Scheraga, H. Equilibrium and kinetic constants for the thiol-disulfide interchange reaction between glutathione and dithiothreitol. *Proc. Natl. Acad. Sci. U. S. A.* **1992**, *89*, 7944–7948.

(50) Fernandes, D. M.; Ghica, M. E.; Cavaleiro, A. M. V.; Brett, C. M. A. Electrochemical impedance study of self-assembled layer-by-layer iron-silicotungstate/poly(ethylenimine) modified electrodes. *Electrochim. Acta* **2011**, *56*, 7940–7945.

(51) Deschaume, O.; Magnin, D.; Cheng, Z. A.; Douchamps, C.; Labbé, P.; Yunus, S.; Durrieu, M.; Nysten, B.; Glinel, K.; Demoustier-Champagne, S.; Jonas, A. M. Comparison of the density of proteins Article